

DE NEEF[®] Cut PURE

Product Description

Cut PURE is a hydrophobic polyurethane designed to fill large voids in rock fissures, gravel layers, joints, and cracks in concrete structures and for the cut-off of gushing water. Depending on the temperature and amount of accelerator (Cut Cat PURE) used, the grout quickly cures to a rigid, closed cell polyurethane foam that is resistant to most organic solvents, mild acids, alkali, petroleum and micro-organisms.

Phthalate free- no phthalate-based plasticizers
Unregulated for transport- no hazmat shipping
Reformulated TDI free-all MDI based technology.
environmentally friendly-NSF/ANSI 61 approved.



CFL PURE when combined with Flex CAT PURE is certified by WQA to NSF/ANSI 61 for materials safety only, as verified and substantiated by test data. Please refer to WQA website (www.wqa.org) for use ratios and limitations.

Product Applications

- Sealing larger volume leaks through concrete cracks and fissures
- Filling voids
- Stabilizing soil or gravel

Product Advantages

- Free Foam Expansion up to 30 times
- Contains no volatile solvents
- Single Component
- Will not dilute in water
- Controlled reaction time
- 3 catalysts available: Cut Cat, Fast, XF

Packaging & Handling

Cut PRe:

- 5 gallon metal pail
- 50 gallon metal drum

Cut Cat PRe:

- 32 oz. metal cans

Cut PRe is sealed under dry nitrogen because it is sensitive to moisture, and should be stored in original containers in a dry area.

Storage temperature must be between 40°F and 90°F. Once the packaging has been opened, the useful life of the material is greatly reduced and should be used as soon as possible. Shelf life: 2 years.

Properties

CUT PURE RESIN		
Solids	100%	ASTM D2369
Viscosity	180 cps at 77°F	ASTM D2196
Color	Black-brown liquid	
Density	1.10 g/cm ³	ASTM D4659
Flashpoint	293°F	ASTM D93
Corrosiveness	Non-corrosive	
Cut Cat PRe		
Viscosity	15 cps at 77°F	ASTM D2196
Color	Red liquid	
Flashpoint	158°F	ASTM D93
Cut PRe Cured		
Density confined	1.00 g/cm ³	ASTM D3574
Density free	2 PCF	ASTM D3574
Compressive strength	35 to 4351 psi	Depends on confinement

Reaction Times

T	% CAT	END REACTION	FOAM FACTOR
40°F	5	5'35"	22V
	10	3'05"	25V
50°F	5	5'00"	24V
	10	2'50"	28V
60°F	5	4'45"	25V
	10	2'35"	28V
68°F	5	4'35"	27V
	10	2'10"	29V
77°F	5	4'00"	28V
	10	2'05"	30V
86°F	5	3'35"	29V
	10	1'55"	30V
95°F	5	2'55"	29V
	10	1'50"	30V

Limitations

Cut PRe must be used with Cut Cat PRe.

Low temperatures will significantly affect viscosity. If site temperatures are extremely low, heat bands or heated water baths may be used on the pails before and during installation to maintain the product's temperature. Avoid splashing water into open containers, as the material is water activated. Avoid exceeding 90°F when warming.

CAUTION: pH NOTICE. Water used to activate PRe Grouts must be in the pH range of 3-10 for optimum foam quality.

Installation Guidelines

Warning: Cut PRe must be used with Cut Cat PRe. Consult the Technical Data Sheets and SDS before using.

Installation Instructions: For detailed installation instructions refer to the DeNeef technical bulletin for your application.

Catalyst: Shake catalyst can 2-3 minutes. Pour the desired amount of Cut PRe into a clean dry pail. Measure the appropriate amount of Cut Cat PRe (refer to the Reaction Times section of this data sheet for the desired set time) and pour it into the pail. Stir until adequately mixed. Exceeding the recommended amount of catalyst may adversely affect the reaction and quality of the cured foam.

Injection: During injection the grout will follow the path of least resistance. When the material has stopped penetrating it will continue to expand against the limits of the confined space and compress within itself, forming a dense, closed cell foam.

Extreme conditions: For application procedures in extreme temperatures and specific environments or equipment recommendations call the DeNeef Technical Service Department.

Cleaning: Clean all tools and equipment which have been in contact with the resin with DeNeef Washing Agent before resin has cured. Products should be disposed of according to local, state, and federal laws.

Health and Safety

Always use protective clothing, gloves and goggles consistent with OSHA regulations. Avoid eye and skin contact. Do not ingest. Refer to SDS. For emergencies, call CHEMTREC 1-800-424-9300.

gcpat.com.br | Brasil Customer Service: 0800 01 47223 | pedidos@gcpat.com

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

Tri-Flex® 15 is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140 USA.

In Canada, GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

Este documento está atualizado somente a partir da última data atualizada indicada abaixo e é válido apenas para uso no Brasil. É importante que você sempre consulte as informações atualmente disponíveis no URL abaixo para fornecer as informações mais atualizadas do produto no momento do uso. Literatura adicional, como Manuais do Empreiteiro, Boletins Técnicos, Desenhos detalhados e recomendações detalhadas, além de outros documentos relevantes, também estão disponíveis em www.gcpat.com.br. As informações encontradas em outros sites não devem ser consideradas, pois podem não estar atualizadas ou aplicáveis às condições em sua localização e não aceitamos qualquer responsabilidade pelo conteúdo delas. Se houver algum conflito ou se você precisar de mais informações, entre em contato com o Serviço de Atendimento ao Cliente do GCP.

Last Updated: 2025-05-13

gcpat.com.br/solutions/products/de-neef-waterproofing-injection-solutions/de-neef-cut-pure