

DE NEEF[®] Flex SLV PURE

Product Description

Flex SLV PURE is an ultra low viscosity hydrophobic polyurethane designed to be injected into hairline cracks in concrete structures. Flex SLV PURE grout expands on contact with water and quickly cures to a tough, flexible foam that is resistant to most organic solvents, mild acids, alkali, petroleum and micro-organisms.

Phthalate free- no phthalate-based plasticizers
Unregulated for transport- no hazmat shipping
Reformulated TDI free-all MDI based technology.
environmentally friendly-NSF/ANSI 61 approved.



C **US**

CFL PURE when combined with Flex CAT PURE is certified by WQA to NSF/ANSI 61 for materials safety only, as verified and substantiated by test data. Please refer to WQA website (www.wqa.org) for use ratios and limitations.

Product Applications

- Sealing fine and hairline leaking cracks in concrete 0.02" and finer
- Injecting grout tubes (INJECTO[®])

Product Advantages

- Super Low Viscosity for hairline cracks
- Free Foam Expansion up to 18 times
- Contains no volatile solvents
- Single Component
- Controlled reaction time
- Improved low temperature performance
- Flex Cat PURE liquid to -40 °F

Packaging & Handling

Flex SLV PURE:

5 gallon metal pail
50 gallon metal drum

Flex Cat PURE:

25 fl. oz. in 1 qt. metal cans

Flex SLV PURE is sealed under dry nitrogen because it is sensitive to moisture, and should be stored in original containers in a dry area. Storage temperature must be between 40 °F and 90 °F. Once the packaging has been opened, the useful life of the material is greatly reduced and should be used as soon as possible. Shelf life: 2 years.

Properties

FLEX SLV PURE RESIN		
Solids	100%	ASTM D2369
Viscosity	200 cps at 77°F	ASTM D2196
Color	Pale yellow	
Density	1.02 g/cm ³	ASTM D4659
Flashpoint	>270°F	ASTM D93
Corrosiveness	Non-corrosive	
FLEX CAT PURE		
Viscosity	15 cps at 77°F	ASTM D2196
Color	Clear to pale grey	
Flashpoint	221 °F	ASTM D93
FLEX SLV PURE CURED		
Density confined	1.00 g/cm ³	ASTM D3574
Density free	about 3 PCF	ASTM D3574
Tensile strength	>174 psi	ASTM D3574
Elongation %	100	ASTM D3574

Reaction Times

T	% CAT	END REACTION	FOAM FACTOR
40°F	2	6'30"	14V
	5	3'25"	16V
60°F	2	5'10"	16V
	5	2'35"	16V
77°F	2	4'30"	16V
	5	2'20"	17V
86°F	2	4'20"	16V
	5	2'00"	17V
95°F	2	3'35"	17V
	5	1'45"	18V

Limitations

Flex SLV PRe must be used with Flex Cat PRe.

Low temperatures will significantly affect viscosity. Flex SLV PRe is not designed for void filling and must be used in compression. If site temperatures are extremely low, heat bands or heated water baths may be used on the pails before and during installation to maintain the product's temperature. Avoid splashing water into open containers, as the material is water activated. Avoid exceeding 90°F when warming.

CAUTION: pH NOTICE. Water used to activate PRe Grouts must be in the pH range of 3-10 for optimum foam quality.

Installation Guidelines

Warning: Flex SLV PRe must be used with Flex Cat PRe. Consult the Technical Data Sheets and SDS before using.

Installation Instructions: For detailed installation instructions refer to the DeNeef technical bulletin for your application.

Catalyst: Shake catalyst can 2-3 minutes. Pour the desired amount of Flex SLV PRe into a clean dry pail. Measure the appropriate amount of Flex Cat PRe (refer to the **Reaction Times** section of this data sheet for the desired set time) and pour it into the pail. Stir until adequately mixed. Exceeding the recommended amount of catalyst may adversely affect the reaction and quality of the cured foam.

Injection: During injection the grout will follow the path of least resistance. When the material has stopped penetrating it will continue to expand against the limits of the confined space and compress within itself, forming a dense, closed cell foam.

Extreme conditions: For application procedures in extreme temperatures and specific environments or equipment recommendations call the DeNeef Technical Service Department.

Cleaning: Clean all tools and equipment which have been in contact with the resin with DeNeef Washing Agent before resin has cured. Products should be disposed of according to local, state, and federal laws.

Health and Safety

Always use protective clothing, gloves and goggles consistent with OSHA regulations. Avoid eye and skin contact. Do not ingest. Refer to SDS. For emergencies, call CHEMTREC 1-800-424-9300.

gcpat.com.br | Brasil Customer Service: 0800 01 47223 | pedidos@gcpat.com

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

Tri-Flex® 15 is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140 USA.

In Canada, GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

Este documento está atualizado somente a partir da última data atualizada indicada abaixo e é válido apenas para uso no Brasil. É importante que você sempre consulte as informações atualmente disponíveis no URL abaixo para fornecer as informações mais atualizadas do produto no momento do uso. Literatura adicional, como Manuais do Empreiteiro, Boletins Técnicos, Desenhos detalhados e recomendações detalhadas, além de outros documentos relevantes, também estão disponíveis em www.gcpat.com.br. As informações encontradas em outros sites não devem ser consideradas, pois podem não estar atualizadas ou aplicáveis às condições em sua localização e não aceitamos qualquer responsabilidade pelo conteúdo delas. Se houver algum conflito ou se você precisar de mais informações, entre em contato com o Serviço de Atendimento ao Cliente do GCP.

Last Updated: 2023-07-07

gcpat.com.br/solutions/products/de-neef-waterproofing-injection-solutions/de-neef-flex-slv-pure